

Laborsil pro 90



Technical Data Sheet

Intended use: Addition-vulcanising kneadable silicone for the universal use in the dental lab with a final hardness of 90 Shore A

Manufacturer: Drewe Dentamid GmbH
Max-Planck-Straße 31
59423 Unna / Germany

Composition:

Pos	Chemical term
1	Polyvinylmethylosiloxane
2	Silicic acid
3	Fillers
4	Polymethylhydrogensiloxane
5	Platin-catalyst
6	Pigments

Properties:

Colour: dark grey

Hardness Shore A: 90 ± 2

Processing time: 1:15 min. at 23°C

Setting time: > 6 min. at 23°C

Consistency: Type 0: kneadable

Recovery from deformation: > 99.2% (ISO 4823)

Deformation under pressure: 3% (ISO 4823)

Linear dimensionel change: < 0.2% (ISO 4823)

Drewe Dentamid GmbH
Max-Planck-Str. 31
59423 Unna / Germany
Tel.: 02303 / 8807-0
Fax: 02303 / 8807-55
dentamid@drewe.de
www.dentamid.drewe.de