

KRACKELERAD GLASYRYTA - VIKTIG INSTALLATIONS- & UNDERHÅLLSINFORMATION

För att skydda och behålla utseendet på den krackelerade glasyrytan är det viktigt att denna instruktion läses och följes.

När plattorna har monterats, men före fogningen, ska plattorna förseglas med en klar penetrerande impregnering, till exempel Fila MP90. Följ tillverkarens användaranvisningar noggrant. Impregneringen förseglar glasyrsprickorna och tillser så att fogen inte tränger in i plattorna. Efter fogning och noggrann rengöring av plattorna, polera bort resterande rester med en ren trasa. Impregnera därefter en ytterligare gång för extra skydd.

OBS! Försegla impregneringen jämnt och noggrant på plattan. Om du använder en kontrasterande fogfärg, kan det vara tillrådligt att göra impregneringen två gånger före fogningen. Följ alltid tillverkarens rekommenderade installationsprocedur och allmänna industristandarder för att säkerställa en lyckad installation.

Använd endast fog av hög kvalitet och gärna med neutral kulör. Försök att sätta plattorna med liten fogbredd (1-2 mm). Detta kakel sätts lämpligen med "tegelsättning", dvs med en halvplattas förskjutning över respektive under en satt platta. Denna platta är gjord på vit lera och varje platta har tillverkats var för sig vilket gör att plattorna har jämna och fina kanter. Vi rekommenderar att dessa glaserade plattor skärs med vått diamantblad för att minska risken för att plattorna går sönder.

Om plattorna ska sitta i våtrum är det väldigt viktigt att försegla plattorna ordentligt eftersom du inte vill att vatten ska tränga in i plattan. Vid skärning med våtsåg kan du uppleva en mörkning av kanterna där vattnet trängt in i plattans kropp. Det är viktigt att plattorna får torka före förseglings- och fogningsprocessen.

OBS! Korrekt impregnering/försegling före och efter fogning är avgörande för projektets framgång. Om du upptäcker en mörkare del av plattan när ytan har utsatts för vatten är plattan antingen inte ordentligt impregnerad eller så finns en vattenläcka bakom plattan. Om du ser detta, låt plattorna torka ordentligt och impregnera därefter ännu en gång. Om det finns vattenläcka måste det omedelbart åtgärdas.

Underhåll av krackelerat kakel bör ske enligt rekommendationer från impregneringstillverkaren.

CRACKLED GLAZE - IMPORTANT INSTALLATION & MAINTANENCE INFORMATION

Due to the inherent nature of Crackled Glaze finishes, they require an additional step in the installation and cleaning process. The crackled finish effect is achieved when the glaze slightly pulls away from the body of the tile creating microscopic cracks in the glaze which allow it to have that antiqued or unique color and texture attributes. To protect and retain this look, prior to applying the tile to the wall, extra care should be exercised to keep the surface of the tile clean.

Once installed and prior to grouting, the tiles should be sealed with a Clear Penetrating Sealer, for example Fila MP90. The manufacturers of the penetrating sealers provide instructions for application which should be followed. This basically seals the glaze cracks and insures that the grout does not penetrate into the tiles during the grout application. After

the grouting and cleaning are completed, be sure to polish off any remaining residue with a clean cloth. It will then be time to once again apply the sealer for additional protection.

NOTE: be sure to seal the surface of the tiles evenly and thoroughly. If using a contrasting color grout, it may be advisable to do the initial sealing twice prior to grouting. Please follow all manufacturers' recommended installation procedures and industry standards to ensure a successful installation.

Use only high quality grout and preferably with neutral color. Try to place the tiles with small joint width (1-2 mm). This tile is appropriately set like bricks, ie with a half tile displacement above or below a set tile. This tile is made of white clay and each tile has been made individually, which makes the tiles even with fine edges. We recommend that these glazed tiles are cut with wet diamond blade to reduce the risk of the plates breaking.

It is of utmost importance to properly seal the tiles in any wet installation since you do not want water to penetrate into the body of the tile. You may experience a darkening of the body of a tile due to water in the cutting process of a wet saw. You may see dark edges on the cuts where the water penetrated the body of the tile. The tile should be allowed to dry prior to the sealing and grouting process.

NOTE: Proper sealing before and after grouting is imperative to the success of the project. If you detect a darkening in the body of the tile when the surface is exposed to water, the tile is either not properly sealed or there is a water leak behind the tile. If you see this, please allow time to dry the tiles and then reseal. If there is a water leak, it must be addressed immediately.

Maintenance of tiles installed in wet areas should be done as recommended by the Sealer Manufacturer.

Använd aldrig ett slipande polermedel på dessa plattor. Använd ett snällt städmedel som rekommenderas av tillverkaren av impregneringen.